

## Modderfontein Laboratory Services (Pty) Ltd

Registration Number : 1966/001741/07

P. O. Box 27

Modderfontein

1645

Tel: +27 011 457 1800

Fax: +27 011 608 0923

Client Name: NJATI HOLDINGS

Gr. No.: 281641

Client Address: P.O.Box 1436

Lims ID: 307429

Fontainbleau

2032

Date Received: 08/03/2021

P.O. No.:

Date Reported: 30/03/2021

Product Name: Richards Bay Gypsum

Batch No.: 08032021

### CERTIFICATE OF ANALYSIS

Test	Test Method	Result	Specification	Unit
Calcium as Ca	MDF 820	20.0	>18	% m/m
Sulphur as S	ALFA 10/1	15.8	>12	% m/m
Total Magnesium as Mg	MDF 820	0.02		% m/m
Water Soluble Magnesium as Mg	MDF 820	0.01		% m/m
CaSO <sub>4</sub> .2H <sub>2</sub> O	Calculation	84.3		% m/m
CaSO <sub>4</sub> .2H <sub>2</sub> O (Dry Basis)	Calculation	97.8		% m/m
pH (10% slurry)	ALFA 19/1	7.8		units
Loss on drying @ 220 °C	Gravimetric	31.4		% m/m
Free Moisture	Gravimetric	13.8		% m/m
Sieve Analysis:<2.0mm	Wet Screening	100.0		% m/m
Sieve Analysis:<0.25mm	Wet Screening	99.9		% m/m
Arsenic as As	MDF 821	<1	50	mg/kg
Cadmium as Cd	MDF 821	0.5	20	mg/kg
Chromium as Cr	MDF 821	1.7	1750	mg/kg
Copper as Cu	MDF 821	18	750	mg/kg
Lead as Pb	MDF 821	6.5	400	mg/kg
Mercury as Hg	MDF 821	<0.5	10	mg/kg
Nickel as Ni	MDF 821	0.9	200	mg/kg
Selenium as Se	MDF 821	<2	15	mg/kg
Zinc as Zn	MDF 821	4.5	2750	mg/kg

Analysis was done on sample as received.

NOTE: 1) CaSO<sub>4</sub>.2H<sub>2</sub>O calculated on dry basis by removing the free moisture content.

2) Calculated results reflect the likely composition.



D. Reddy

Fertilizer Manager

Disclaimer: MLS is an Agrilasa certified Laboratory for fertilizer. MLS is certified under ISO 9001 (Certificate #LS1804). MLS is responsible for management of all information obtained and /or created during performance of service and shall treat it as confidential. MLS strives to undertake all activities or services impartially

